



LORD WOOL 4190

 FULLY
MADE IN ITALY

COMPOSITION: 80% Ww 20% Pl
 WIDTH: 140 cm
 WEIGHT: 570 gr./mtl

USE: 

CARE: 

MARTINDALE END POINT: 18.000 rubs
 UNI EN ISO 12947-2:2000 12 Kpa

COLOUR FASTNESS TO LIGHT: >5
 UNI ISO 105-B02:2004

DETERMINATION OF SPILLAGE RESISTANCE: weft/warp 3,2 mm
 UNI EN ISO 13936-1:2004 warp/weft 3,2 mm

PILLING TEST:
 UNI EN ISO 12945-2:2002 (Martindale Method C)

step 1	500 rubs	4
step 2	1.000 rubs	4
step 3	2.000 rubs	3/4
step 4	5.000 rubs	3/4

All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel srl, any infringement of this rights will be pursued vigorously.