

PRINCE 4191



COMPOSITION 80% Wv 20% PI

WIDTH 140 cm

WEIGHT 550/570 gr/mtl



MARTINDALE END POINT 30.000 rubs
UNI EN ISO 12947-2:200 12 KPA

COLOUR FASTNESS TO LIGHT >5
UNI EN ISO 105-BO2:2004

DETERMINATION OF SLIPPAGE RESISTANCE Weft/Warp 3,2 mm
UNI EN ISO 13936-2:2004 Warp/Weft 3,2 mm

PILLING TEST Step 1 500 rubs 4
UNI EN ISO 12945-2:2002 Step 2 1.000 rubs 4
(Martindale Method C) Step 3 2.000 rubs 3/4
Step 4 5.000 rubs 3/4

FLAMEPROOF TEST **USA** TB117:2003 California Test
GB BS 5852-1:1979 Cigarette and Match
EN EN 1021-1:2014 Cigarette EN 1021-2:2004 and Match



All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel srl. Any infringement of this rights will be pursued vigorously.
© Icons from Noun Project - Yusuf - Azam Ishaq - Youngky Kurniawan (CC BY 3.0)