

Composition: 67% Vi 20% Co 13% Pl

Pile Composition: 100% Vi

Width: 140 cm

Weight: 820-840 gr/mlt



Martindale end point: 30.000 rubs


UNI EN ISO 12947-2:2000 12 kpa

Colour fastness to light: 4

UNI ISO 105-BO2:2004

Determination of slippage resistance: weft/warp 4,1 mm

UNI EN ISO 13936 - 2:2004 warp/weft 3,9 mm



All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel 2.0 srl, any infringement of this rights will be pursued vigorously.